

## Main Chemical Composition

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	TiO <sub>2</sub>	CaO	MgO	Na <sub>2</sub> O+K <sub>2</sub> O	L.O.I
35-40	27-31	14-18	<2	<0.5	<0.5	<0.5	11-12

<b>Type of Material:</b>	Refractory Clay
<b>Refractoriness (PCE):</b>	>1650 <sup>o</sup> C
<b>Major Phase:</b>	Kaolinite - Boehmite
<b>Minor Phase:</b>	Hematite – Anatase - Calcite
<b>Physical Properties:</b>	abrasive Weak conductivity (heat and electricity)
<b>Available Size (mm):</b>	0-300

**Description:** High Alumina Refractory Clay containing a high proportion of aluminosilicate Kaolinite and Iron. It can be used in Ceramic, Cement or Abrasive industries as raw material.

**Packing:** Bulk.

**Storage:** Store in dry location.

*Note: The above-mentioned data represent typical values obtained from current production and are subject to normal variation or individual tests. This result cannot be considered min or max for specific purposes.*



Tel: +98 21 88716301-2 +98 21 88556293

Fax/WhatsApp: +98 21 88706146



WWW.SEMIROM-MINE.COM

info@semirom-mine.com



Head Office: 5<sup>th</sup> floor- No 82- 31<sup>st</sup> Avenue – Ebnesina street – Yousef Abad – Tehran - IRAN