



SEMIRAW-R

Main Chemical Composition

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	CaO	MgO	Na ₂ O+K ₂ O	L.O.I
31-34	36-39	13-15	<2	<0.5	<0.5	<0.5	11-12

Type of Material:	Refractory Clay
Refractoriness (PCE):	>1650 ^o C
Major Phase:	Kaolinite
Minor Phase:	Hematite – Anatase - Boehmite
Available Size (mm):	0-300

Description: High Alumina Refractory Clay containing a high proportion of aluminosilicate Kaolinite and Iron. It can be used in Ceramic, Cement or Abrasive industries as raw material.

Packing: Bulk.

Storage: Store in dry location.

Note: The above-mentioned data represent typical values obtained from current production and are subject to normal variation or individual tests. This result cannot be considered min or max for specific purposes.



Tel: +98 21 88716301-2 +98 21 88556293

Fax/WhatsApp: +98 21 88706146



WWW.SEMIROM-MINE.COM

info@semirom-mine.com



Head Office: 5th floor- No 82- 31st Avenue – Ebnesina street – Yousef Abad – Tehran - IRAN