

SEMIROM-LI

Main Chemical Composition

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	CaO	MgO	Na ₂ O+K ₂ O	L.O.I
44-45	51-53	<1.1	<2	<0.5	<0.5	<0.5	<0.15

Type of Material:	Low Iron Chamotte
Refractoriness (PCE):	>1700 ^o C
Major Phase:	Mullite
Minor Phase:	Cristobalite – Hematite – Rutile – Glassy Phase
Water Absorption %	<2
Bulk Density (gr/cm³)	2.7-2.76
Physical Properties:	Low Iron Low porosity High density Excellent thermal stability Good thermal shock resistance High mechanical resistance Good Corrosion resistance
Available Size (mm):	0-1 1-3 3-5 0-12 (BULK) Powder (75-100 μm)

Description: Chamotte also known as ‘grog’, ‘firesand’ or “fireclay” is calcined clay containing a high proportion of alumina. It is produced by firing selected fire clays in a rotary kiln to temperatures between 1,250°C and 1,300°C, before grinding and screening to specific particle sizes. For refractories, chamotte contains from 38% to 48% alumina in general. Iron is generally limited to 1% and alkalis must be also limited in amount to preserve refractoriness and thermal stability at high temperatures.

Packing: 1.2-1.3 Tone Big bags.

Storage: Store in dry location.

Note: The above-mentioned data represent typical values obtained from current production and are subject to normal variation or individual tests. This result cannot be considered min or max for specific purposes.



Tel: +98 21 88716301-2 +98 21 88556293

Fax/WhatsApp: +98 21 88706146



WWW.SEMIROM-MINE.COM

info@semirom-mine.com



Head Office: 5th floor- No 82- 31st Avenue – Ebnesina street – Yousef Abad – Tehran - IRAN