



SEMIGUN 60-10S

Description: A refractory Gunning Mass consisting of calcined, Abrasion resistant aggregates bonded with high purity calcium aluminate cement. Developed for use in Alkali zone such as burner of rotary kilns & etc. Adaptable for casting or Gunning. Excellent alkali resistance and Strength throughout its entire temperature range, High resistance to Mechanical impact and Abrasion.

Type of Material:	High Alumina Gunning Mass
Bonding System:	Hydraulic
Raw Material Base:	Rotary Bauxite -Chamotte – High Alumina Cement – Silicon Carbide
Max Service Temperature:	1500 ^o C
Installation Method:	Casting - Gunning
Grain Size:	0-6 mm
Dry Material Required:	2.4 ton/m ³
Drinking Water Required on site:	10-12%

Main Chemical Composition based on Raw Materials

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	SiC
55-60	20-22	<1	3-5	5-8

Physical Properties

	Bulk Density (gr/cm ³)	PLC (%)	CCS (Mpa)	MOR (Mpa)
After Drying @ 110 ^o C/24 hrs.	>2.52	-	60-90	7-8
After Firing @ 1550 ^o C / 3 hrs.	>2.50	0-0.5	60-90	7.5-8.5

Drying and Heating: Cured for 24 hours before removing molds, dry at 110°C for 24-36 hours. heating to working temperature at 25-50°C/h.

Packing: 25 kg Multi wall water proof sacks. Palletized 48 sacks per pallets. Protected with stretch wrap.

Storage: Beyond 9 months is not recommended. Store in dry location.

Note: The above-mentioned data represent typical values obtained from current production using ASTM standard and are subject to normal variation or individual tests. This result cannot be considered min or max for specific purposes.



Tel: +98 21 88716301-2 +98 21 88556293

Fax/WhatsApp: +98 21 88706146



WWW.SEMIROM-MINE.COM

info@semirom-mine.com



Head Office: 5th floor- No 82- 31st Avenue – Ebnesina street – Yousef Abad – Tehran - IRAN